



Phones: +381 63 658 074 / +381 64 27 54 268

Email: info@decachem.com

TECHNICAL DATA SHEET

Coconut shell granular activated carbon



Gold refining
Gold recovery
Metallurgy



Description

After water grinding and dust removal, it has higher wear resistance, stronger adsorption performance, and no residual powder. The gold loss rate is extremely low, which greatly reduces the cost of mining.

It is suitable for gold refining methods such as heap leaching, magma method, and electrolytic adsorption.

Specification

Particle size	6×12 mesh	> 6 mesh	< 4%
		< 12 mes	< 4%
Platelets AARL	≤7%		
Attrition AARL	≤1.5%		
Iodine value	1050 mg/g		
Specific surface area	1100 m ² /g		
CTC	55		
K value	28%		
R value	60%		
Bulk density	500±20 kg/m ³		
Ash content	3%		
Moisture	4%		
Hardness	99%		



DECACHEM DOO, Novi Sad, Serbia

Address: Lozionicka 14/9, 21000 Novi Sad, Serbia ;
PIB: 113353206 Matični broj: 21851396

[Http://www.decachem.com](http://www.decachem.com)



Phones: +381 63 658 074 / +381 64 27 54 268

Email: info@decachem.com

Package

25kg or 500kg per bag



Transportation



DECACHEM
LETS GROW!